

International Scientific Organization http://iscientific.org/ Chemistry International www.bosaljournals.com/chemint/



# Activated carbon from molasses efficiency for Cr(VI), Pb(II) and Cu(II) adsorption: A mechanistic study

K. Legrouri<sup>1,2</sup>, E. Khouya<sup>1,3,\*</sup>, H. Hannache<sup>1</sup>, M. El Hartti<sup>1</sup>, M. Ezzine<sup>1</sup> and R. Naslain<sup>4</sup>

<sup>1</sup>Laboratoire d'Ingénierie et Matériaux (LIMAT), Equipe des Matériaux Thermo-Structuraux et Polymères, Université Hassan II, Faculté des Sciences Ben M'Sik, B.P. 7955, Casablanca, Morocco <sup>2</sup>Institut Supérieur des Professions Infirmières et Techniques de Santé, Agadir, Morocco

<sup>3</sup>Centre Régional des Métiers de l'Education et de la Formation, Sous Massa, Inzegane, Morocco

<sup>4</sup>Laboratoire des Composites Thermostructuraux, UMR-580 (CNRS-Snecma-CEA-UB1), Domaine universitaire,3 allée de la

Boétie, 33600 Pessac Bordeaux, France

\*Corresponding author's E. mail: e.khouya@gmail.com

# ARTICLE INFO

Article type: Research article Article history: Received October 2016 Accepted January 2017 July 2017 Issue Keywords: Molasses Activated carbon Phosphoric acid Adsorption Metal ions

# ABSTRACT

Activated carbon was prepared from molasses, which are natural precursors of vegetable origin resulting from the sugar industry. A simple elaboration process, based on chemical activation with phosphoric acid, was proposed. The final product, prepared by activation of molasses/phosphoric acid mixture in air at 500°C, presented high surface area (more than 1400 m<sup>2</sup>/g) and important maximum adsorption capacity for methylene blue (625 mg/g) and iodine (1660 mg/g). The activated carbon (MP2(500)) showed a good potential for the adsorption of Cr(VI), Cu(II) and Pb(II) from aqueous solutions. The affinity for the three ions was observed in the following order Cu<sup>2+</sup>> Cr<sup>6+</sup>> Pb<sup>2+</sup>. The process is governed by monolayer adsorption following the Langmuir model, with a correlation coefficient close to unity.

© 2017 International Scientific Organization: All rights reserved. **Capsule Summary:** The study present the result of adsorption of Cr(VI), Cu(II) and Pb(II) by an activated carbon prepared by chemical activation of molasses with phosphoric acid. A good potential for adsorption of three ions was observed.

**Cite This Article As:** K. Legrouri, E. Khouya, H. Hannache, M. El Hartti, M. Ezzine and R. Naslain. Activated carbon from molasses efficiency for Cr(VI), Pb(II) and Cu(II) adsorption: A mechanistic study. Chemistry International 3(3) (2017) 301-310.

# INTRODUCTION

The increasing use of heavy metals in industrial activities has caused contamination of natural waters. For example, chromium, lead, cadmium and copper are found in wastewater effluents of industries such as electroplating, plastic and paint manufacturing, mining, metallurgical process, petrochemical process, batteries, paper and pulp (Oboh et al., 2009; Iqbal, and Edyvean, 2004; Bennett et al., 2001; Iqbal, 2007; Kim et al., 2003; Roque-Malherbe et al., 2007).

At least 20 metals are classified as toxic and half of them are released into the environment in large quantities leading to risks for human health (Iqbal et al., 2005; Kortenkamp et al., 1996). The hexavalent chromium is considered among the very toxic compounds and may cause lung cancer. While Cr(III) is relatively innocuous and immobile, Cr(VI) moves readily through soils and aquatic environments and is a strong oxidizing agent capable of being absorbed through the skin (Kortenkamp et al., 1996; Demirbas, 2004; Wu, 2008; El Harti, 2013ab). Lead is toxic to living organisms and can bioaccumulate and enter the food chain when released into the environment. It is known to cause mental retardation, reduces haemoglobin production, necessary for oxygen transport, and interferes with normal cellular metabolism, which causes damaging effects on body nervous system (Barbooti et al. 2015; El Harti, 2013; Momčilović et al., 2011; Hassan et al., 2014; Li et al. 2010; Acharya et al., 2009; Swiatkowski et al. 2004). Excess copper is known to be highly toxic to sweet potato, with concentrations as low as 5  $\mu$ M in the root zone being sufficient to cause significant growth reduction (Roque-Malherbe et al. 2007). At concentrations above 20  $\mu$ M, prevention root growth and death of the transplanted cutting may result (El Harti, 2013a; Mahmood et al. 2015).

Conventional methods for removing metals from industrial effluents include chemical precipitation, coagulation, solvent extraction, electrolysis, membrane separation (Gürel et al. 2005), ion – exchange (Roque-Malherbe et al. 2007; Barbooti, 2010; Gaikwad et al., 2010) and adsorption on different materials (El Harti et al., 2013ab; Al-Jlil, 2009).

The idea of using various agricultural products and by-products for the removal of heavy metals from aqueous solutions has been investigated by several researchers (Bouchelta et al., 2008; Chowdhury et al., 2012; Billy et al., 2013; Ahmedna et al., 2000; Hassan et al., 2013). The efficiency of different organic waste materials as sorbents for heavy metals has been proven, with the obvious advantage of their lower cost compared to other materials (Carrott et al., 2007; Wu et al., 2008; Giwa et al., 2013). Activated carbon appears to be particularly competitive and effective for the removal of heavy metals at trace quantities (Acharya et al. 2009; Li et al., 2010; Hassan et al., 2014; Momčilović et al., 2011).

The aim of this work is to test the removal of heavy metal ions, such as Cr(VI), Pb(II) and Cu(II), by activated carbon prepared from molasses, which are the secondary products of the sugar industry. The importance of this study is ducted by the abundance of this by-product and the important results obtained previously on the activation of molasses by sulfuric acid (K. Legrouri et al., 2001; K. Legrouri et al., 2005; K. Legrouri et al., 2012). The activating agent used in this study was phosphoric acid, which is known by its catalytic properties, and the conditioning variables examined were temperature and heating time. The properties of the activated carbon thus prepared were examined by determination of the maximal adsorption capacity of methylene blue and iodine, BET surface area measurement and scanning electron microscopy observation. The adsorption tests on the three ions, Cu(II), Pb(II) and Cr(VI), were affected by the best material obtained in this study.

#### **MATERIAL AND METHODS**

# **Reagents and chemicals**

All chemicals were of analytical reagent grade and no further purification was required. Double-distilled water was used for dilution purpose. The element standard solutions for calibration were prepared by diluting a stock solution of 1000 mg.L<sup>-1</sup>.

#### Methods

The elemental analyses were carried out by a GBC 908 PBMT atomic absorption spectrophotometer. All measurements were carried out in an air/acetylene flame.

Specific surface areas of the solid materials were measured by the BET method (Brunauer et al., 1938). The samples were degassed at 160°C for 24 h. A pH-metre Mini 80 (Tacussel, France), equipped with a combined glass electrode and a graduated burette of 0.05 mL, was used.

The surface image of both activated adsorbent was taken with a JED JSM-840 ALGS analytical scanning electron microscope (SEM).

### Heavy metal ion solutions

The working stock solutions (1000 mg.L<sup>-1</sup>) of Cu(II), Pb(II) and Cr(VI) were prepared by dissolving an exact amount of CuSO<sub>4</sub>·5H<sub>2</sub>O, Pb(NO<sub>3</sub>)<sub>2</sub> and K<sub>2</sub>Cr<sub>2</sub>O<sub>7</sub> in distilled water and further diluted as required. The pH values were adjusted by dropwise addition of concentrated HNO<sub>3</sub>.

#### Preparation of activated carbon [MP2 (500)]

The precursor used to prepare the activated carbon is molasses and the activation was completed by activation by phosphoric acid. The choice of the precursor and its processing were dictated by two reasons: the molasses is composed essentially by organic matter (more than 90% after dehydration) and the chemical activation by phosphoric acid presents several advantages, amongst which are of lower temperature, shorter time of activation, and higher yield of activated carbon compared to physical activation (Bouchelta et al., 2008).

The weight ratio of the mixture of molasses and phosphoric acid (80%) was of  $H_3PO_4$ /precursor = 2. After pre-processing at 120°C in an oven for two hours, the mixture was heated in a furnace at 500°C under air. The choice of the activating agent and the weight ratio was based on previous studies by the authors (Legrouri et al. 2001; Legrouri et al., 2005). The thermally treated product, referred to as MP2(500), was washed with distilled water in a Soxhlet extractor, to eliminate excess acid and soluble matter, then dried at 110°C. Before use in adsorption tests. the adsorbent was sieved and more than 95% of the final particles had an average diameter of 100 µm. The performance of MP2(500) activated carbon was evaluated by determination of the maximal adsorption capacity for methylene blue and iodine, the specific surface area (SBET), the surface functions and the morphology by scanning electron microscopy.

#### Properties of [MP2(500)]



Fig. 1: Scanning electron micrograph of MP2 (500)

The specific surface area ( $S_{BET}$ ), the total surface acidity and the Electron Microprobe Analysis (EMPA) data for MP2(500) are presented in Tables 1 and 2. The parameters of the adsorption isotherm for methylene blue (MB) and iodine are given in Table 3.

The results mentioned in Tables 1, 2 and 3 show an improvement of textural and structural properties of MP2(500). The values in Table 2 reveal the important rate of carbon and oxygen due to carbonization of the precursor and the formation of the carbon skeleton. The presence of phosphorus suggests the incorporation of this element in the structure of the adsorbent and the formation of C-O-P bonds (Guo et al., 2007; Shrestha Rajeshwar et al. 2012). The value of the specific surface area of the activated carbon exceed 1470 m<sup>2</sup>/g (Table 1) and the maximum adsorption capacity is higher than 600 mg/g for MB and 1600 mg/g for iodine (Table 3). Besides, the development of the functional surface groups and total acidity is observed (Table 1).

The microtexture observation of MP2(500) by SEM (Figure 1) shows significant morphology differences among the samples. The development of porosity accounts for the values obtained in adsorption tests and specific surface area values.

#### Effect of pH on adsorption

The effect of initial pH on metal ion adsorption was studied by using 100 mL of a 10 mg/L aqueous solution of either

**Table 1:** Summary of characteristics values of the prepared activated carbon MP2(500)

Functional groups in surface (meq/g)					
Carboxylic	Lactone	Hydroxyl			
0.85	0.10	0.78			
Total surface acidity	Total surface basic	Sbet			
(meq/g)	(meq/g)	(m <sup>2</sup> g <sup>-1</sup> )			
1.73	0.32	1477			

Cu(II), Pb(II) or Cr(VI) and 15 mg of activated carbon. The mixture was stirred at the constant rate of 150 rpm in a temperature controlled orbital shaker maintained at 30°C. The initial pH (pH<sub>0</sub>) of the adsorbate solution was adjusted using 1 N HNO<sub>3</sub> or 1 N NaOH aqueous solution without any further adjustment during the sorption process. The mixtures were withdrawn at the end of predetermined time values, *t*, their contents centrifuged, using a research centrifuge at 5000 rpm for 5 min, and the supernatant liquid was diluted, if required, with double distilled water and analysed for using residual metal absorption ions atomic spectrophotometry. The quantity of removed metal ions (removal percentage) was calculated using relation shown in Eq. 1.

$$R(\%) = \left[\frac{(c_0 - c_f)}{c_0}\right].100$$
(1)

Where, *R* is metal ions recovery (%),  $C_o$  and  $C_f$  (mg/L) are initial (t<sub>0</sub>) and final (t<sub>f</sub>) concentrations of metal ions, respectively.

# **Adsorption kinetics**

The two important physicochemical aspects for the evaluation of the sorption process, as a unit operation, are the kinetics and the equilibrium time of sorption. For kinetics studies, 100 mg/L of adsorbent was added to 500 mL of

**Table 2:** The electron microprobe values of activated carbon MP2(500)

The electron microprobe values (% atomic)						
С	0	Si	Р	Cu		
87.37	6.73	0.67	2.89	2.36		

aqueous solutions containing 25 mg/L of Cu(II) or 23.4 mg/L of Pb(II) or 24.3 mg/L of Cr(VI). After adjustment of the pH to the desired value, the mixture was shaken at room temperature. The adsorption kinetics was followed for 6 h and it was observed that after 15 min of contact time, the rate of removal of the adsorbate from the solution was gradual and very slow. The present removal of a metal ion at time  $t_i$  was calculated using relation shown in Eq. 2.

$$R_i(\%) = \left[\frac{(C_0 - C_i)}{C_0}\right]. \ 100 \tag{2}$$

Where,  $R_i$  is metal ions recovery at t<sub>i</sub>, C<sub>0</sub> and C<sub>i</sub> (mg/L) are the liquid phase concentrations of metal ions at initial moment (t<sub>0</sub>) and time (t<sub>i</sub>), respectively

#### **RESULTS AND DISCUSSION**

#### Effect of solution pH

The pH of the solution is an important factor in determining the rate of surface reactions (Carrott P. J. M, and Ribeiro Carrott M. M. L., 2007). Figure 2 shows the influence of the initial pH values of  $Cu^{2+}$ ,  $Pb^{2+}$  and  $Cr_2O_7^{2-}$  solutions on their



**Fig. 2:** The starting solution pH influence on the adsorption by MP2 (500) of  $Cu^{2+}$ , Pb<sup>2+</sup> and Cr<sub>2</sub>O<sub>7</sub><sup>2-</sup>



**Fig. 3:** Kinetics adsorption of  $Cu^{2+}$ ,  $Pb^{2+}$  and  $Cr_2O_7^{2-}$  on MP2 (500) (Conditions:  $C_0$  (Cu) = 25 mg/L;  $C_0$  (Pb) = 23.4 mg/L;  $C_0$  ( $Cr_2O_7^{2-}$ ) = 24.3 mg/L, pH = 6.2, pH = 3.8, pH = 1.8)

adsorption by MP2(500). The first observation is that the adsorption of the three heavy metal ions is strongly controlled by the pH values of the starting solution. The sorption of Cu<sup>2+</sup> increases with increasing pH. The maximum adsorption (58%) was reached at pH 6.3 indicating the important effect of the solution pH on the adsorption of this ion. The sorption of Pb<sup>2+</sup> is very important at pH 4, with an adsorption rate close to 100%. For the dichromate ions (Cr<sub>2</sub>O<sub>7<sup>2-</sup></sub>), the adsorption is favoured at low pH values and becomes more important at pH 2.

Cu<sup>2+</sup> and Pb<sup>2+</sup> (effect of pH)

At pH values lower than 3, there is excessive protonation of the carbon surface resulting in a decrease in the adsorption of Pb<sup>2+</sup> and Cu<sup>2+</sup> (M<sup>2+</sup>) (Ghaedi M. and Mosallanejad N. 2013, Saifuddin M. Nomanbhay and Kumaran P. 2005). On increasing the pH of M<sup>2+</sup> solutions from 3, the percentage removal increased and become quantitative over the pH range 3-6. It is known that divalent metal ions (M<sup>2+</sup>) can be present in water at different forms such as M<sup>2+</sup>, M(OH)<sup>+1</sup>, M(OH)<sub>2</sub><sup>0</sup>, M(OH)<sub>3</sub><sup>-1</sup>, etc. (Bryant P. S., Olaniyi I. et al. 2012). At a pH  $\leq$  3, the predominant lead and coper species is always M<sup>2+</sup> and the M<sup>2+</sup> removal is mainly accomplished by sorption process (Gaikwad R. W. et al., 2010). The increase in metal removal as pH increased can be explained on the basis of a decrease in competition between proton (H<sup>+</sup>) and positively charged metal ion at the surface sites, and by decrease in positive charge which results in a lower repulsion of the adsorbing metal ion.

Thus, the fact that more  $M^{2+}$  sorption took place at a higher pH could be attributed to a decrease in competition between H<sup>+</sup> and M<sup>2+</sup> at the same sorption site of MP2(500). Furthermore, the surface of MP2(500) is more negatively charged at a higher pH, which causes a more electrostatic attraction of M<sup>2+</sup>.

# Cr(VI) (effect of pH)

The pH dependence of chromium adsorption can largely be related to the type and ionic state of the functional groups present on the activated carbon MP2(500) and the chromium ions chemistry in solution (Zainul A. Z. et al. 2009). In the pH range of 1- 6, chromium ions coexists in different forms such as  $Cr_2O_7^{2-}$ ,  $HCrO^{4-}$ ,  $Cr_3O_{10}^{2-}$ ,  $Cr_4O_{13}^{2-}$  of which  $HCrO_{4^-}$  predominates (Covarrubias C. et al., 2005).

The favorable effect at low pH can be attributed to the neutralization of negative changes on the surface of the adsorbents by excess hydrogen ions, thereby facilitating the diffusion of the hydrogen chromate ion (HCrO<sub>4</sub>-) and its subsequent adsorption, because HCrO<sub>4</sub>- is the dominant anionic form of Cr(VI) between pH 1.0 and 4.0. This ionic form was found to be preferentially adsorbed on the surface of carbon. The negative charges could result from oxygenated functional groups of basic character such as lactone or hydroxyl groups, chemisorbed at the surface of the pores. The possible explanation for higher adsorption in the acidic region is that the Cr<sub>2</sub>O<sub>7</sub><sup>2-</sup> ion is oxidized to Cr<sup>3+</sup> (Karthiheyan et al., 2005).

As the pH of the solution increases, the predominant species are then  $CrO_4^{2-}$  and  $Cr_2O_7^{2-}$ . More adsorption at acidic pH indicates that the lower pH results in an increase in H<sup>+</sup> ions on the adsorbent surface that result in significantly strong electrostatic attraction between positively charged adsorbent surface and chromate ions. Lesser adsorption of Cr(VI) at pH values greater than 6.0 may be due to the dual competition of both the anions ( $CrO_4^{2-}$  and  $OH^-$ ) to be adsorbed on the surface of the adsorbent, of which  $OH^$ predominates. This is in accordance with earlier studies that reported the removal of Cr(VI) by different adsorbents (Gardea-Torresdey J. L. et al. 2000, Liu S. X. et al. 2007, Mohan D. and Pittman C. U. 2006, Schneider R.M. et al. 2007).

#### **Adsorption kinetics**

In order to evaluate the adsorption characteristics of MP2(500) for Cu<sup>2+</sup>, Pb<sup>2+</sup> and Cr<sub>2</sub>O<sub>7</sub><sup>2-</sup> ions, the change of their adsorption rate with time has been investigated (Figure 3). The adsorption rate of the three ions on MP2(500) rises rapidly at the initial stage of adsorption reaching about 75%, 52% and 28% for Pb<sup>2+</sup>, Cr<sub>2</sub>O<sub>7</sub><sup>2-</sup> and Cu<sup>2+</sup>, respectively, after 30 min of contact time (more than 50% of maximum adsorption rate). No appreciable increase in adsorption rates was observed beyond this time and the equilibrium adsorption was essentially reached within 120 min.

#### Adsorption isotherms

The adsorption isotherm indicates how the quantities of target species are distributed between the liquid and the solid phases when the adsorption process reaches equilibrium. It is employed to establish the maximum capacity of adsorption of metals on adsorbents, which is expressed in term of metal quantity adsorbed per unit of used adsorbent mass (mg/g or mmol/g).

Different amounts of MP2(500) (between 250 and 1000 mg/L) were added to 250 mL aqueous solutions containing 50 mg/L of Cr(VI) or Pb (II) or 70 mg/L of Cu(II). The mixture was stirred for 8 hours in a batch reactor at atmospheric pressure and constant temperature. The pH was maintained around to desired value of each solution by addition of 0.1 M NaOH or 0.1 M HCl. When the equilibrium was reached, the residual concentration of each ion was measured. Figure 4 shows the isotherms of adsorption of the three ions.

The curves can be classified into two categories according to the classification of Giles et al. (1974):

- Adsorption isotherms of the Pb(II) and Cu(II) are concave curves reversed downwards, which can be classified in the L category. This type of isotherm shows a decrease in the active sites as the solute adsorption progresses. This phenomenon occurs when the attractive forces between the adsorbed species are low, which results in a monolayer adsorption of species in an isolated manner;
- ii) The adsorption isotherm of the chromate ion, which is of S type, is characterized by an upwards concavity. The adsorbed species favour the subsequent adsorption of other molecules (cooperative adsorption). This is due to attractions between these species by Van Der Waals forces, which make them grouped into blocks that are bunched together against each other.

The adsorption isotherms of the three ions were well fitted by the Langmuir and Freundlich models (Freundlich, 1906; Treybal, 1968; Ho and McKay, 1998). The linear forms of the Langmuir and Freundlich isotherms are represented by the equations 3 and 4, respectively.



**Fig. 5:** Langmuir (upper) and Freundlich (lower) Plots of three ions (Cr(VI), P(II) and Cu(II) adsorbed by MP2 (500)

$$\frac{C_e}{q_e} = \left(\frac{1}{K_L Q_m}\right) + \left(\frac{1}{Q_m}\right) C_e \tag{3}$$

Where,  $K_L$  = Langmuir equilibrium constant for adsorption (L/mg),  $Q_m$  = maximum adsorption capacity (mg/g),  $Q_e$  = amount adsorbed at equilibrium (mg/g),  $C_e$  = equilibrium concentration (mg/L).

$$\ln q_e = \ln K_F + \frac{1}{n \ln C_e} \tag{4}$$

Where,  $K_F$  and n are the isotherm constants of the Freundlich equation.

The isotherm constants of Freundlich and Langmuir were calculated from the plots of  $C_e/qe$  versus  $C_e$  and  $\ln q_e$  versus  $\ln C_e$ , respectively (Figure 5), and the results are listed in Table 4.

It is clear that the correlation coefficients (R<sup>2</sup>) for the Langmuir isotherm are slightly higher than that for the Freundlich isotherm, which indicates that the uptake occurs on a homogenous surface by monolayer adsorption and can be described in terms of chemisorption (bond formation between adsorbent and adsorbate) (Gregg and Sing, 2000). The essential characteristics of Langmuir isotherm can be expressed by a dimensionless constant called equilibrium



**Fig. 4:** isotherms of adsorption of the three ions (Cu(II), Cr(VI) and Pb(II)) on (MP2 (500))

The order of adsorption affinity based on the amount of metal ion uptake (mg metal ion/g of activated carbon) is as follows:  $Cu^{2+}>Pb^{2+}> Cr^{6+}$  (Table 4). The values of maximum adsorption capacity by the Langmuir model equal 144.93 mg/g, 303.03 mg/g and 526.32 mg/g for Cr(VI), Pb(II) and Cu(II), respectively. The importance of the values of  $q_m$  is attributed to the high surface area of MP2(500), which is more than 1400 m<sup>2</sup>.g<sup>-1</sup>. The difference of the adsorption capacity between the three metal ions is due to the form, size and electrical charge of the ions. The Cu(II) ion has a spherical form and a too small size compared to those of the Pb(II) ion and the dichromate ion (most dominant ion at pH around 4). Furthermore, the surface functional groups, existing on the surface of the activated carbon, are rich in carbonyl group which promotes the strong attractive interactions between the cations and the active surface of the MP2(500).

Table 3: Summary of isotherm parameters of adsorption of methylene blue (MB) and iodine by MP2(500)

$Q^{\circ}(mgg^{-1})$ $b_1$ $K_f$ $N$ $Q^{\circ}(mgg^{-1})$ $b_1$	Elovich	
	2	
MB 625 1,45 399 0,166 270 0,1	98	
Iodine         1666         0,285         786         0,166         910         0,0	28	

Table 4: Isotherm parameters obtained for the adsorption of Cr(VI), Pb(II) and Cu(II) ions onto MP2(500)

Metal	Langmuir					Freundlich			
Ions	q <sub>m</sub> (mg/g)	$b_1$	$R_{\rm L}$	R <sup>2</sup>	K <sub>f</sub>	Ν	1/n	R <sup>2</sup>	
Cr(VI)	144.93	0.248	0.544	0.996	2.056	0.596	1.68	0.980	
Pb(II)	303.03	0.030	0.398	0.998	12.508	1.340	0.746	0.993	
Cu(II)	526.32	0.030	0.340	0.999	20.538	1.350	0.741	0.979	

parameter,  $R_L$  (Langmuir, 1918; Ferrero, 1907) which is defined by:

$$R_{L} = \frac{1}{1 + bC_0} \tag{5}$$

Where, *b* is the Langmuir constant and  $C_0$  the initial concentration (mg/L).  $R_L > 1 = Unfavorable$  adsorption,  $0 < R_L < 1 = Favorable$  adsorption,  $R_L = 0 = Irreversible$  adsorption,  $R_L = 1 = Linear$  adsorption,  $R_L$  value between 0 and 1 indicated favourable adsorption.

The adsorption of the three ions followed the Langmuir model for the present systems indicated the formation of monolayer coverage of adsorbate at the outer surfaces of the adsorbent. Likewise, it may be stated that the ion retention by MP2(500) was ruled by physisorption as well as a cationic exchange process. It was found that the metal ion uptake by MP2(500) increased with increasing initial metal ion concentrations.

Generally, the mechanisms of heavy metal ion adsorption on activated carbon were very complicated and appear attributable to physical adsorption, electrostatic attraction, precipitation and chemical interaction between the heavy metal ions and the surface functional groups. In our case, two mechanisms are most likely. The first is the intra granular distribution for heavy metal ions of small size which limits the activated carbon adsorption capacity (case of copper ions adsorption). The second is the chemical interaction and the electrostatic attraction between metal ions and the surface functional groups formed by chemical activation of MP2(500). This latter is the major adsorption mechanism in our case (Selomulya et al., 1999; Mohan et al. 2005; Demiral et al., 2008; Mohan and Pittman, 2006; Agarwal et al., 2006). The existence of various surface functional groups, such as basic, phenolic, carboxyl, carbonyl and hydroxyl groups (Meunier et al., 2003; Tee and Khan, 1988; Annadurai et al., 2002), on the surface of MP2(500) increased the adsorption amount of the three metal ions. Some suggestive mechanisms

for the adsorption of Cu(II), Pb(II) and Cr(VI) are electrostatic attraction (physical adsorption) and chemical interaction between the heavy metals ions and the surface functional groups of MP2(500). In view of MP2(500) efficiency, it could be used for the remediation pollutant of environmental concern (Akram et al., 2017; Babarinde et al., 2016; Babarinde and Onyiaocha, 2016; Bhatti et al., 2016; Iqbal et al., 2013; Iqbal, 2016; Iqbal et al., 2015; Iqbal and Bhatti, 2015; Iqbal et al., 2016; Iqbal and Nisar, 2015; Iqbal et al., 2017; Jamal et al., 2015; Manzoor et al., 2013; Mushtaq et al., 2017; Qureshi et al., 2015; Rashid et al., 2016; Sayed, 2015; Shindy, 2016; Shindy et al., 2016; Shoukat et al., 2017; Tahir et al., 2016a; Tahir et al., 2016b; Ullah et al., 2013).

# CONCLUSIONS

The experimental results of the adsorption of Cu(II), Cr(VI) and Pb(II) metal ions on the activated carbon (MP2(500)) prepared from molasses are encouraging. The adsorbent may be used for the removal of the metal ions from aqueous solutions. The adsorption tests indicate the affinity of MP2(500) for the ions in the following order Cu<sup>2+</sup>> Cr<sup>6+</sup>> Pb<sup>2+</sup>. The adsorption of the three ions is governed by monolayer adsorption given that the correlation coefficient (R<sup>2</sup>) of the Langmuir model is close to unity.

#### ACKNOWLEDGEMENTS

The Authors sincerely appreciate financial support from Hassan II academy of science and technology (2011-2014). Also, Authors appreciated valuable discussion from Prof. Roger Naslain x-director of Thermostructural Composites Laboratory UMR5801 (CNRS-Snecma-UB1-CEA).

### REFERENCES

- Acharya, J., Sahu J.N., Mohanty, C.R., Meikap, B.C., 2009. Removal of lead (II) from wastewater by activated carbon developed from Tamarind wood by zinc chloride activation. Chemical Engineering Journal 149, 249-262.
- Agarwal, G.S., Bhuptawat, H.K., Chaudhari, S., 2006. Biosorption of aqueous chromium (VI) by Tamarindus indica seeds. Bioresource Technology 97(7), 949-956.
- Ahmedna, M., Marshall, W.E., Rao R.M., 2000. Granular activated carbons from agricultural by-products: preparation, properties and application in sugar refining, Bulletin of Lousiana State University Agricultural Centre, 54.
- Akram, M., Bhatti, H.N., Iqbal, M., Noreen, S., Sadaf, S., 2017. Biocomposite efficiency for Cr(VI) adsorption: Kinetic, equilibrium and thermodynamics studies. Journal of Environmental Chemical Engineering 5, 400-411.

- Al-Jlil, S.A., Alsewailem, F.D., 2009. Saudi Arabian Clays for Lead Removal in Wastewater, Applied Clay Science 42, 671-674.
- Annadurai, G., Juang, R.S., Lee, D.L., 2002. Adsorption of heavy metals from water using banana and orange peels. Water Science Technology 47(1), 185-190
- Arbooti Mahmood, M., 2015. Simultaneous Removal of Chromium and Lead from Water by Sorption on Iraqi Montmorillonite, Journal of Environmental Protection 6, 237-249
- Babarinde, A., Ogundipe, Kemi, Sangosanya, K.T., Akintola, B.D., Elizabeth Hassan, A.-O., 2016. Comparative study on the biosorption of Pb(II), Cd(II) and Zn(II) using Lemon grass (Cymbopogon citratus): kinetics, isotherms and thermodynamics. Chemistry International 2, 89-102.
- Babarinde, A., Onyiaocha, G.O., 2016. Equilibrium sorption of divalent metal ions onto groundnut (Arachis hypogaea) shell: kinetics, isotherm and thermodynamics. Chemistry International 2, 37-46.
- Barbooti, M.M., Zablouk, M., Al-Zubaidi, U.A., 2010. Recovery of Chromium from Waste Tanning Liquors by Magnesium Oxide, International Journal of Industrial Chemistry 1, 29-38.
- Bennett, P.M., Jepson, P.D., Law, R.J., Jones, B.R., Kuiken, T., Baker, J.R., Rogan, E., Kirkwood, J.K., 2001. Exposure to heavy metals and infectious disease mortality in harbour porpoises from England and Wales. Polish Journal of Environmental Studies 112, 33-40.
- Bhatti, H.N., Zaman, Q., Kausar, A., Noreen, S., Iqbal, M., 2016. Efficient remediation of Zr(IV) using citrus peel waste biomass: Kinetic, equilibrium and thermodynamic studies. Ecological Engineering 95, 216-228.
- Billy, T.H., Puziah Abdul Latif, G., Taufiq., Yap, Y.H., 2013. Physical preparation of activated carbon from sugarcane bagasse and corn husk and its physical and chemical characteristics. International Journal of Engineering Sciences & Research Technology 2, 1-14.
- Bouchelta, C., Salah Medjram, M., Bertrand, O., Bellat, J.P., 2008. Preparation and characterization of activated carbon from date stones by physical activation with steam, Journal of Analytical and Applied Pyrolysis 82, 70-77.
- Brunauer, S., Emmett, P.H., Teller, E., 1938. Adsorption of gases in multi-molecular layers, Journal of the American Chemical Society 60, 309-319.
- Bryant, P.S., Petersen, J.N., Lee, J.M., Brouns, T.M., 1992. adsorption of hexavalent chromium by red fir sawdust. Applied Biochemistry and Biotechnology 34-35, 777-788.

- Carrott, P.J.M, Ribeiro Carrott, M.M.L., 2007. Use of low cost biosorbent as lignin for adsorption and purification waste water. Journal of Technology 98, 2301-2312.
- Chowdhury, Z.Z., Zain, M.S., Atta Khan, R., Arami-Niya, A., Khalid, K., 2012. Process variables optimization for preparation and characterization of novel adsorbent from lignocellulosic waste, Bioresource Technology 7, 3732-3754.
- Covarrubias, C., Arriagada, R., Yanez J., Garcia, R., 2005. Removal of chromium(III) from tannery effluents, using a system of packed columns of zeolite and activated carbon, Journal of Chemical Technology and Biotechnology 80, 899–908.
- Demiral, H., Demiral, I., Tümsek, F., Karabacakoğlu, B., 2008. Adsorption of chromium(VI) from aqueous solution by activated carbon derived from olive bagasse and applicability of different adsorption models, Chemical Engineering Journal 144(2008), 188–196.
- Demirbas, E., Kobya, M., Senturk, E., Ozkan, T., 2004. Adsorption Kinetics for the Removal of Chromium (VI) from Aqueous Solutions on the Activated Carbons Prepared from Agricultural, Wastes. Water SA, 30, 533-539.
- El Harti, M., Hannache, H., Khouya E., Oumam, M., Fakhi, S., Djafari, D., Hanafi, N., Zarrouk A., 2013. Removal of lead (II) by adsorption onto moroccan oil shale of timahdit:
  Effect of pH, contact time and equilibrium isotherm analyses, Der Pharmacia Lettre 5, 132-139
- El Harti, M., Hannache, H., Khouya, E., Hanafi, N., El Bouchti, M., Zarrouk, A., Fakhi, S., Afrin, L., Saoiabi, A., Hammouti, B., 2013. Hexavalent chromium removal from aqueous solution by adsorbent prepared from Moroccan oil shale of Timahdit, Der Pharmacia Lettre 5, 338-346
- Ferrero, F., 2007. Dye removal by low cost adsorbents, hazelnut shells in comparison with wood sawdust. Journal of Hazardous Materials 142(1), 144-152
- Freundlich, H.Z., 1906. Over the adsorption in solution, The Journal of Physical Chemistry 57, 384-470
- Gaikwad, R.W., Sapkal, R.S., Sapkal, V.S., 2010. Removal of Copper Ions from Acid Mine Drainage Wastewater Using Ion Exchange Technique: Factorial Design Analysis. Journal of Water Resource and Protection 2, 984-989.
- Gardea-Torresdey, J.L., Tiemann, K.J., Armendariz, V., Bess-Oberto, L., Chianelli, R. R., Rios, J., Parsons, J.G., Gamez, G., 2000. Characterization of Cr(VI) binding and reduction to Cr(III) by the agricultural byproducts of Avenamonida (oat) biomass, Journal of Hazardous Materials 80, 175– 188.

- Ghaedi, M., Mosallanejad, N., 2013. Removal of Heavy Metal Ions from Polluted Waters by Using of Low Cost Adsorbents, J. Chem. Health Risks 3(1), 07-22.
- Giles, C.H., Smith, D., Huitson, A., 1974. A general treatment and classification of Colloid and Interface Science 47, 755-765
- Giwa, A.A., Bello, I.A., Oladipo, M.A., Adeoye, D.O., 2013. Removal of Cadmium from Waste-water by Adsorption Using the Husk of Melon (Citrullus lanatus) Seed, Int. J. of Basic and Applied Science 2 (1), 110-123.
- Gregg, S.J., Sing, K.S.W., 1982. Adsorption, Surface Area and Porosity, (2nd Ed.) Academic Press – London.
- Guo, Y., Rockstraw, D.A., 2007. Physicochemical properties of carbons prepared from pecan shell by phosphoric acid activation, Bioresource Technology 98, 1513-1521.
- Gürel, L., Altaş, L., Büyükgüngör, H., 2005. Removal of Lead from Wastewater Using Emulsion Liquid Membrane Technique, Environmental Engineering Science 22, 411-420.
- Haimour, N.M., Emeish, S., 2006. Utilization of date stones for production of activated carbon using phosphoric acid, Waste Management 26, 651-660.
- Hassan, A.F., Youssef, A.M., 2014. Preparation and characterization of microporous NaOH activated carbons from hydrofluoric acid leached rice husk and its application for lead(II) adsorption, Carbon Letters 15, 57-66.
- Hassan, A.F., Youssef, A.M., Priecel, P., 2013. Removal of deltamethrin insecticide over highly porous activated carbon prepared from pistachio nutshells. Carbon Letters 14, 234-246.
- Ho, Y.S., McKay G., 1998. Sorption of dye from aqueous solution by peat. Chemical Engineering Journal 70, 115– 124
- Iqbal, J.M., Cecil, F., Ahmad, K., Iqbal, M., Mushtaq, M., Naeem, M.A., Bokhari, T.H., 2013. Kinetic study of Cr(III) and Cr (VI) biosorption using Rosa damascena phytomass: a rose waste biomass. Asian Journal of Chemistry 25, 2099.
- Iqbal, M., 2016. Vicia faba bioassay for environmental toxicity monitoring: a review. Chemosphere 144, 785-802.
- Iqbal, M., Abbas, M., Arshad, M., Hussain, T., Khan, A.U., Masood, N., Tahir, M.A., Hussain, S.M., Bokhari, T.H., Khera, R.A., 2015. Gamma radiation treatment for reducing cytotoxicity and mutagenicity in industrial wastewater. Polish Journal of Environmental Studies 24, 2745-2750.
- Iqbal, M., Bhatti, I.A., 2015. Gamma radiation/H 2 O 2 treatment of a nonylphenol ethoxylates: degradation, cytotoxicity, and mutagenicity evaluation. Journal of Hazardous Materials 299, 351-360.

- Iqbal, M., Edyvean R.G.J., 2004. Biosorption of lead, copper and zinc ions on loofa sponge immobilized biomass of Phanerochaete chrysosporium, Minerals Engineering 17, 217 - 223.
- Iqbal, M., Edyvean, R.G.J., 2005. Loofa sponge immobilized fungal biosorbent: A robust system for cadmium and other dissolved metal removal from aqueous solution. Chemosphere 61, 510-518.
- Iqbal, M., Edyvean, R.G.J., 2007. Ability of loofa spongeimmobilized fungal biomass to remove lead ions from aqueous solution, Pakistan Journal of Botany 39(1), 231-238,
- Iqbal, M., Iqbal, N., Bhatti, I.A., Ahmad, N., Zahid, M., 2016. Response surface methodology application in optimization of cadmium adsorption by shoe waste: A good option of waste mitigation by waste. Ecological Engineering 88, 265-275.
- Iqbal, M., Nisar, J., 2015. Cytotoxicity and mutagenicity evaluation of gamma radiation and hydrogen peroxide treated textile effluents using bioassays. Journal of Environmental Chemical Engineering 3, 1912-1917.
- Iqbal, M., Nisar, J., Adil, M., Abbas, M., Riaz, M., Tahir, M.A., Younus, M., Shahid, M., 2017. Mutagenicity and cytotoxicity evaluation of photo-catalytically treated petroleum refinery wastewater using an array of bioassays. Chemosphere 168, 590–598.
- Jamal, M.A., Muneer, M., Iqbal, M., 2015. Photo-degradation of monoazo dye blue 13 using advanced oxidation process. Chemistry International 1, 12-16.
- Kim, Y., Lee, B., Yi, J., 2003. Preparation of Functionalized Mesoporous Silica Containing Magnetite (MSM) for the Removal of Copper Ions in Aqueous Solutions and its Magnetic Separation. Separation Science and Technology 38, 2533-2548.
- Kortenkamp, A., Casadevall, M., Faux, S. P., Jenner, A., Shayer, R.O.J., Woodbridge, N., O'Brien, P., 1996. A role for molecular oxygen in the formation of DNA damage during the reduction of the carcinogen chromium (VI) by glutathione. Archives of Biochemistry and Biophysics 329(2), 199-208.
- Langmuir, I., 1918. The adsorption of gases on plane surfaces of glass, mica and platinum. Journal of the American Chemical Society 40, 1361-1403.
- Legrouri, K., El Harti, M., Oumam, M., Khouya, E., Wahbi, R., Hannache, H., Zarrouk, A., 2012. Characterization and evaluation performance of activated carbon prepared from coconut shell argan, Journal of Chemical and Pharmaceutical Research 4(12), 5081-5088
- Legrouri, K., Ezzine, M., Hannache, H., Denoyel, R., Pallier, R., Naslain, R., 2001. Removal of organic and inorganic

pollutants by activated carbon elaborated from molasses. Annales de Chimie Science des Matériaux 26, S383-S389

- Legrouri, K., Khouya, E., Ezzine, M., Hannache, H., Denoyel, R., Pallier, R., Naslain, R., 2005. Production of activated carbon from a new precursor molasses by activation with sulphuric acid, Journal of Hazardous Materials B118, 259–263.
- Li, Y., Du, Q., Wang, X., Zhang, P., Wang, D., Wang, Z., Xia, Y., 2010. Removal of lead from aqueous solution by activated carbon prepared from Enteromorpha prolifera by zinc chloride activation. Journal of Hazardous Materials 183, 583-589.
- Liu, S.X., Chen, X., Chen, X.Y., Liu, Z.F., Wang H.L., 2007. Activated carbon with excellent chromium (VI) adsorption performance prepared by acid-base surface modification, Journal of Hazardous Materials 141, 315– 319.],
- Manzoor, Q., Nadeem, R., Iqbal, M., Saeed, R., Ansari, T.M., 2013. Organic acids pretreatment effect on Rosa bourbonia phyto-biomass for removal of Pb (II) and Cu (II) from aqueous media. Bioresource Technology 132, 446-452.
- Meunier, N., Laroulandie, J., Blais, J.F., Tyagi, R.D., 2003. Cocoa shells for heavy metal removal from acidic solutions, Bioresource Technology 90, 255-263
- Mohan, D., Singh, K.P., Singh, V.K., 2005. Removal of hexavalent chromium from aqueous solution using lowcost activated carbons derived from agricultural waste materials and activated carbon fabric cloth, Industrial & Engineering Chemistry Research 44, 1027–1042.
- Mohan, D., Pittman, U., 2006. Activated carbons and low cost adsorbents for remediation of tri and hexavalent chromium from water, Journal of Hazardous Materials 137, 762 - 811.
- Momčilović, M., Purenović, M., Bojić, A., Zarubica, A., Ranđelović, M., 2011. Removal of lead(II) ions from aqueous solutions by adsorption onto pine cone activated carbon. Desalination 276, 53.
- Mushtaq, M., Bhatti, H.N., Iqbal, M., Noreen, S., 2016. Eriobotrya japonica seed biocomposite efficiency for copper adsorption: Isotherms, kinetics, thermodynamic and desorption studies. Journal of Environmental Management 176, 21-33.
- Nadeem, R., Manzoor, Q., Iqbal, M., Nisar, J., 2016. Biosorption of Pb (II) onto immobilized and native Mangifera indica waste biomass. Journal of Industrial and Engineering Chemistry 35, 185-194.
- Nisar, J., Sayed, M., Khan, F.U., Khan, H.M., Iqbal, M., Khan, R.A., Anas, M., 2016. Gamma – irradiation induced degradation of diclofenac in aqueous solution: Kinetics, role of

reactive species and influence of natural water parameters. Journal of Environmental Chemical Engineering 4, 2573-2584.

- Nouren, S., Bhatti, H.N., Iqbal, M., Bibi, I., Kamal, S., Sadaf, S., Sultan, M., Kausar, A., Safa, Y., 2017. By-product identification and phytotoxicity of biodegraded Direct Yellow 4 dye. Chemosphere 169, 474-484.
- Oboh, I., Aluyor, E., and Audu, T., 2009. Biosorption of heavy metal ions from aqueous solutions using a biomaterial. Leonardo Journal of Sciences 14, 58–65
- Olaniyi I., Moses, S., Raphael, O., 2012. Adsorption study of Cr (VI) and Pb (II) from aqueous solution using animal charcoal derived from cow bone, Der Chemica Sinica 3(3), 648-657
- Qureshi, K., Ahmad, M., Bhatti, I., Iqbal, M., Khan, A., 2015. Cytotoxicity reduction of wastewater treated by advanced oxidation process. Chemistry International 1, 53-59.
- Rashid, A., Bhatti, H.N., Iqbal, M., Noreen, S., 2016. Fungal biomass composite with bentonite efficiency for nickel and zinc adsorption: a mechanistic study. Ecological Engineering 91, 459-471.
- Roque-Malherbe, R.M.A., Duconge, H.J.J., Del Valle, W., Toledo, E., 2007. Lead, Copper, Cobalt and Nickel Removal from Water Solutions by Dynamic Ionic Exchange in LECA Zeolite Beds. International Journal of Environment and Pollution 31, 292-303.
- Saifuddin, M., Nomanbhay, K.P., 2005. Removal of heavy metal from industrial wastewater using chitosan coated oil palm shell charcoal, Electronic Journal of Biotechnology 8(1), 43-53.
- Sayed, M., 2015. Efficient removal of phenol from aqueous solution by the pulsed high-voltage discharge process in the presence of H<sub>2</sub>O<sub>2</sub>. Chemistry International 1, 81-86.
- Schneider, R.M., Cavalin, C.F., Barros, M.A.S.D., Tavares, C.R.G., 2007. Adsorption of chromium ions in activated carbon, Chemical Engineering Journal 132(1–3), 355-362.
- Selomulya, C., Meeyoo, V., Amal, R., 1999. Mechanisms of Cr(VI) removal from water by various types of activated carbons, Journal of Chemical Technology & Biotechnology 74, 111- 122.
- Shindy, H., 2016. Basics in colors, dyes and pigments chemistry: A review. Chemistry International 2, 29-36.
- Shindy, H., Goma, M., Harb, N., 2016. Novel carbocyanine and bis carbocyanine dyes: synthesis, visible spectra studies, solvatochromism and halochromism. Chemistry International 2, 222-231.
- Shoukat, S., Bhatti, H.N., Iqbal, M., Noreen, S., 2017. Mango stone biocomposite preparation and application for

crystal violet adsorption: A mechanistic study. Microporous and Mesoporous Materials 239, 180-189.

- Shrestha Rajeshwar, M., Yadav Amar, P., Pokharel Bhadra, P., Ram, P.R., 2012. Preparation and Characterization of Activated Carbon from Lapsi (Choerospondias axillaris) Seed Stone by Chemical Activation with Phosphoric acid, Research Journal of Chemical Sciences 2(10), 80-86.
- Swiatkowski, A., Pakula, M., Biniak, S., Walczyk, M., 2004. Influence of the surface chemistry of modified activated carbon on its electrochemical behaviour in the presence of lead (II) ions, Carbon 42, 3057-3069.
- Tahir, M.A., Bhatti, H.N., Iqbal, M., 2016a. Solar Red and Brittle Blue direct dyes adsorption onto Eucalyptus angophoroides bark: Equilibrium, kinetics and thermodynamic studies. Journal of Environmental Chemical Engineering 4, 2431-2439.
- Tahir, N., Bhatti, H.N., Iqbal, M., Noreen, S., 2016b. Biopolymers composites with peanut hull waste biomass and application for Crystal Violet adsorption. International Journal of Biological Macromolecules 94, 210-220.
- Tee, T.W., Khan, R.M., 1988. Removal of lead, cadmium and zinc by waste tea leaves, Environmental Technology Letters 9, 1223-1232
- Treybal, R.E., 1968. Mass transfer operations, 2<sup>nd</sup> ed., McGraw Hill, New York.
- Ullah, I., Nadeem, R., Iqbal, M., Manzoor, Q., 2013. Biosorption of chromium onto native and immobilized sugarcane bagasse waste biomass. Ecological Engineering 60, 99-107.
- Wu, Y., Zhang, S., Guo, X., Huang, H., 2008. Adsorption of chromium(III) on lignin. Bioresource Technoloogy 99, 7709.
- Zainul, A.Z., Marlini, S., Nurfadilah, M., Wan, A.A., 2009. Chromium(VI) removal from aqueous solution by untreated rubber wood sawdust, Desalination 244, 109– 121.

Visit us at: http://bosaljournals.com/chemint/ Submissions are accepted at: editorci@bosaljournals.com